



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 27, 2024

Ms. Evelyn Sura
DAZIAN, LLC
89 Leuning Street D-2
South Hackensack, NJ 07606

Reference: Laboratory Test Report
Lab Identification No. 60344
Invoice No. 91637

Dear Ms. Sura:

One (1) fabric sample, identified as **Spacer**, was received and tested in accordance with the test procedures outlined. The results are as follows:

Test Results

<u>Test Procedures</u>	
Bursting Strength (lbs./sq.in) ASTM D 3786-18 (Mullen)	200.0+
Bursting Strength (lbf) ASTM D 3787-16 (Ball)	340.0
Taber Abrasion ASTM 3884-22 CS-17 wheels, 500 gram load	Passed 12,667 Cycles

Sincerely,

Brian S. Dement

BSD/mr

